Amendments to the Specification:

Page 1, line 1, delete the word "SPECIFICATION".

Page 1, please insert the following as the first paragraph:

This application is a U.S. National Phase Application under 35 USC 371 of International Application PCT/JP2002/012113, filed November 20, 2002.

Page 17, replace paragraph [0026] (Table) with:

[0026]

•	MS O R3	
Exemplified	R³ ·	M
compound S-3-1	-C ₂ H ₅	—н
S-3-2	-CH2-CH=CH2	- #
-500	Cli _y =ClinCli _y =Cliy=	
9-3-3		—H
S-3-4	-C7H15	_ H
S-3-5	-CgH ₁₈	-Na
S-3-6		—н
S-3- 7	—C ₄ H ₉ (t)	— H
S-3-8	-NHCH ₃	 #
S-3-0	-n	—н
S-3-10	N—N	—н
S-3-11	-NH-	—н
S-3-12	—NH———CH3	—н
S-3-13	-NHCOCH ₃	—н
\$-3-14	-NHSO ₂	—н
S-3-15	-N(CH ₃)₂	—н
S-3-16		—Н
S-3-17	-CH ₂ -	—н
S-3-18	-s-cH ₃	—H
S-3-19	-s-	—н
S-3-20	—sH	—н

Page 18, replace paragraph [0027] (Table) with:

[0027]

	MS S R3	
Exemplified compound 8-3-21	NN R ³ H	. М —н
S-3-22	—C₂H₃	—н
\$-3-23	—C ₄ H ₉ (t)	—н
S-3-24	C ₆ H ₁₃	—н
S-3-25		 H
S-3-26	NO3	—н
S-3-27	-N(CH ₃)₂	—н
S-3-28	-\bigs_\mathrew\rightarrow\righta	—н
S-3-29	—NH—	—н
		- الم
9-3-30	NHN(CH ₃) ₂	—н
\$-3-31	-CH ₂ CH=CH ₂	—н
S-3-32	SH	—н
S-3-33	-NHCOC ₂ H ₅	н

Page 43, replace the third paragraph starting with "Solution
A2" and ending with "Water to make 420 ml", as follows:

Solution A2

Sodium chloride

71.9 g

K₂IrCl₆

 $K_2[IrCl_6]$

 4×10^{-8} mol/mol AgX

K₄Fe (CN) €

 K_4 [Fe(CN)₆]

2x10⁻⁵ mol/mol AgX

Potassium bromide

0.7 g

Water to make

420 ml

Pages 77-78, replace paragraph [0128] (Table) with:

Sample	Sensi-	Fogging	Gradation	Storage	Pressure	Re-
No.	tivity	Fogging	(γ)	stability	resistance	marks
101	100	100	100	145	E	Comp.
102	110	93	115	137	D	Comp.
103	108	92	114	132	D	Comp.
104	110	95	119	135	E	Comp.
105	117	86	125	116	С	Inv.
106	118	87	126	114	C	-Inv
107	121	84	129	108	В	Inv.
108	140	71	139	86	A-	Inv.
109	142	70	137	83	A	Inv.
110	141	70	138	86	A	Inv.
111	136	74	130	90	В	Inv.
112	135	73	131	87	В	Inv.
113	137	73	133	88	A	Inv.
114	143	70	133	83	A	Inv.
115	134	74	131	88	В	Inv.
116	135	75	130	89	В	Inv.
117	133	73	133	87	A	Inv.
118	136	73	130	86	В	Inv.
119	129	77	128	96	В	Inv.
120	128	82	126	106	С	Inv.
121	147	70	141	81	A	Inv.

Page 86, replace paragraph [0143] (the Table) with:

[0143]

Sample No.	Clarity of thin lines and text	Flesh color repro- ducibility	Vegetation green repro- ducibility	Print repro- ducibility	Remarks
101	D	D	ם	D	Comp.
102	D	C	С	ם	Comp.
103	D	С	С	D	Comp.
104	D	D	Q	С	Comp.
105	В	В	В	В	Inv.
106	В	В	В	В	Inv.
107	A	А	В	В	Inv.
108	A	A	A	A	Inv.
109	<u> </u>		λ	<u> </u>	Inv.
110	A	A ·	A	A	Inv.
111	A	В	В	B	Inv.
112	A	В	В	В	Inv.
113	A	В	В	В	Inv.
114	A	A	A	A	Inv.
115	В	В	A	В	Inv.
116	В	A	B	В	Inv.
117	B	A	В	В	Inv.
118	В	A	В	В	Inv.
119	A	В	A	В	Inv.
120	В	В	В	В	Inv.
121	A	A	A	A	Inv.

Page 88, replace paragraph [0145] (the Table) with:

[0145]

Sample No.	Clarity of thin lines and text	Flesh color repro- ducibility	Vegetation green repro- ducibility	Print repro- ducibility	Remarks
101	D	D	D	D	Comp.
102	D	C.	C .	D	Comp.
103	D	С	C	. D	Comp.
104	D.	D	D	С	Comp.
105	В	В	В	В	Inv.
106	В	В	В	В	Inv.
107	A	A	В	В	Inv.
108	A	A	A	A	Inv.
109	A	A	Α	A	Inv
110	A .	A	A	A	i Inv.
111	В	В	A	В	Inv.
112	В	В	A	В	Inv.
113	В	В	A	В	Inv.
114	A	A	A	A	Inv.
115	В	В	A	В	Inv.
116	В	A	В	В	Inv.
117	В	A	В	В	Inv.
118	В	A	В	В	Inv.
119	A	В	A	В	Inv.
120	В	В	В	В	Inv.
121	A	A	A	A	Inv.